

CLAIMS

1. A vinyl chloride resin composition for vehicles comprising 100 parts by mass of a vinyl chloride resin and 5 to 200 parts by mass, in total, of (A) at least one trimellitic ester plasticizer and (B) at least one sebacic ester plasticizer, the mass ratio of component (A) to component (B) being 99/1 to 60/40.
5
2. The vinyl chloride resin composition for vehicles according to claim 1, wherein the trimellitic ester plasticizer (A) is an ester compound derived from a single or mixed alcohol having 7 to 10 carbon atoms.
3. The vinyl chloride resin composition for vehicles according to claim 1 or 2,
10 wherein the sebacic ester plasticizer (B) is an ester compound derived from a single or mixed alcohol having 8 to 10 carbon atoms.
4. The vinyl chloride resin composition for vehicles according to any one of claims 1 to 3, further comprising 0.001 to 5 parts by mass of a perchloric acid salt.
5. The vinyl chloride resin composition for vehicles according to any one of
15 claims 1 to 4, which is used in powder molding.